

Appendix 2

Sound absorption coefficient according to EN-ISO 11654

Measurement of sound absorption coefficient in a reverberation room

Client: Saint-Gobain Ecophon AB
 Description: ODS 45 mm
 Date of test: 2023-12-01

Object: Acoustic board for Fade, 40 mm.
 Base layer of type Ecophon Fade Duo Primer.
 Surface layer of type Ecophon Fade Duo Top

Empty reverberation room: Reverberation room with object:

Relative humidity: 80,2 % Relative humidity: 79,1 %
 Temperature: 17,9 °C Temperature: 18,2 °C
 Barometric pressure: 98,5 kPa Barometric pressure: 98,5 kPa

Surface area: 10,80 m²
 Room volume: 200,0 m³
 Total room area S_i: 211,4 m²

Frequency f [Hz]	α_s 1/3 octave
50	0,01
63	0,03
80	0,06
100	0,12
125	0,23
160	0,49
200	0,64
250	0,77
315	0,80
400	0,80
500	0,99
630	0,95
800	0,83
1000	0,87
1250	0,88
1600	0,85
2000	0,88
2500	0,87
3150	0,84
4000	0,81
5000	0,83

Appendix 2

Sound absorption coefficient according to EN-ISO 11654

Measurement of sound absorption coefficient in a reverberation room

Client: Saint-Gobain Ecophon AB Date of test: 2023-12-01
 Description: ODS 45 mm

Object: Acoustic board for Fade, 40 mm.
 Base layer of type Ecophon Fade Duo Primer.
 Surface layer of type Ecophon Fade Duo Top

Empty reverberation room:	Reverberation room with object:
Relative humidity: 80,2 %	Relative humidity: 79,1 %
Temperature: 17,9 °C	Temperature: 18,2 °C
Barometric pressure: 98,5 kPa	Barometric pressure: 98,5 kPa

Surface area:	10,80 m ²
Room volume:	200,0 m ³
Total room area S _r :	211,4 m ²

Frequency f [Hz]	α _p 1/1 octave
100	
125	0,30
160	
200	
250	0,75
315	
400	
500	0,90
630	
800	
1000	0,85
1250	
1600	
2000	0,85
2500	
3150	
4000	0,85
5000	

Frequency f [Hz]	Practical sound absorption coefficient α _p
125	0.30
250	0.75
500	0.90
1000	0.85
2000	0.85
4000	0.85

Weighted sound absorption coefficient according to ISO 11654

α_w = 0,90 Classification: A